



Edge Sealer

1. General Description

Laykold Masters Edge Sealer is a two component, thixotropic polyurethane based sealer.

Basic Use: Laykold Masters Edge Sealer is designed to seal porous rubber mats prior to the application of polyurethane coatings.

2. Safety Guidelines

Always wear the recommended personal protective equipment. Avoid contact with eyes, skin, and clothing. Adequate ventilation is required during application.

3. Storage and Packaging

Laykold Masters Edge Sealer should be kept dry, cool, and in original packaging. Laykold Masters Edge Sealer has a shelf life of 1 year.

Packaging: 20 kg kit (approximately 4 gallon unit)

4. Coverage

Laykold Masters Edge Sealer coverage is approximately 0.60-1.20 kg/m² (0.17-0.34 gal/yd² or 26-53 ft²/gal).

5. Installation Guidelines

The surface must be clean, dry, and free of oil, grease, dirt, and any foreign residue.

Laykold Masters Edge Sealer Part A and B must be power mixed. Pre-mix the color component, empty the small component into the larger container, mix thoroughly prior to application, for at least 2-4 minutes (depending on design of power equipment and application conditions), in order to obtain uniform blending. In order to obtain uniform coverage, Laykold Masters Edge Sealer should be applied with a flat trowel.

Features and Benefits

- ✓ No VOC
- ✓ Thixotropic
- ✓ Easy application
- ✓ Excellent sealer
- ✓ Composed of more than 40% renewable resources



6. Limitations

- Minimum surface and application temperature: 10°C (50°F)
- Maximum surface and application temperature: 54°C (130°F)
- Do not apply over wet substrate
- Sealed surfaces should be coated within 24 hours

7. Technical Data

Results based on temperature of 23°C (73°F) and 50% Humidity

VOC	0 g/L*
Renewable Resources	41.2%
Density	1.26-1.32 g/cm ³
Viscosity	Thixotropic
Color	Grey
Mixing Ratio by Weight (A:B)	4:1
Pot Life	35-55 minutes
Tack Free Time	5-6 hours
Shore A Hardness	65-85

*Based on standard formula calculation

Above figures are guide values and should not be used as a base for specifications

Consult the Safety Data Sheet (SDS) for more details

For complete and latest warranty and product information, please visit www.advpolytech.com

